

Starting Formulation

SF 8001

Solventless, Pre-Preg Matrix System for Fiber Reinforced Composites EPON™ Resin 828

Introduction This solventless epoxy binder is designed for prepreg graphite or glass tape and sheet stock subsequently compression molded into high performance composites required to perform on a long term basis at temperatures as high as 300 °F. A variation of this formulation utilizing MEK and BF3MEA accelerator is commonly used to produce printed circuit board laminates meeting the NEMA G-11 specification.

- Features**
- Pre-pregs exhibit good retention of tack and draping characteristics when stored at room temperature
 - High interlaminar shear strengths and transverse tensile strengths
 - Relatively short press cure required

Formula	Material	Supplier	Pounds	Gallons
Formulation				
	EPON Resin 828	Westlake Epoxy Specialty Chemical	100.0	10.38
	4, 4' Diaminodiphenyl Sulfone	RSA Corp.	<u>32.5</u>	<u>2.93</u>
	Total Formulation		132.5	13.31

Compounding and Impregnation The DADPS curing agent is dissolved with agitation into EPON Resin 828 at a temperature of 275-300 °F. Once a clear solution has been obtained, the blend is reduced in temperature to 175-200 °F. Viscosity is sufficiently low in this temperature range for rapid wetting and impregnation of graphite tow or glass roving. Heating of guide rollers and squeeze rollers facilitates maximum impregnation.

The impregnated fiber may be "B"-staged to a tacky, drapable consistency by heating for a period of approximately 10 minutes in a forced draft oven or drying tower at a temperature of 250 °F. The prepreg should be sandwiched between release film for storage. The tack retention life of the prepreg should be approximately 4 weeks at 88 °F and in excess of 12 months at 0 °F.

Typical Handling Properties Table 1 / Handling Properties

	Units	Value
Viscosity, Brookfield		
at 140 °F	cP	2,000
at 200 °F	cP	180
Working Life		
at 140 °F	hrs	8
at 200 °F	hrs	5
Pounds/Gallon	lbs/gal	9.55
Pre-Cure at contact pressure ¹		
Time	hrs	<1.5
Platen or Autoclave Temperature	°F	275

Generated: March 28, 2024
Issue Date:
Revision:

© and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Pressure Cure

Initial	1 hour @ 275 °F and 100 psi
Final	2 hours @ 350 °F and 100 psi
Post Cure	
Option 1	1 hour @ 400 °F
Option 2	7 hours @ 350 °F

excessive squeeze-out when
of the binder may be
eliminated when lower pressure

¹ The purpose of this step is to polymerize the binder almost to the gel point in order to prevent pressure is applied and to provide sufficient back pressure to expel any entrapped air. Thickening followed by probing an open end of the lay-up. This pre-cure step is usually shortened or molding techniques such as vacuum bagging are used to fabricate the composites.

Matrix Properties Table 3 / Properties of Cast Matrix System¹

	<u>Units</u>	<u>Value</u>
Physical Strength Properties		
Tensile Strength	psi	12,500
Tensile Elongation	%	3.2
Tensile Work ³	in.•lbs/in.	409
Tensile Modulus	psi	0.55x10 ⁶
Flexural Strength		
at 77 °F	psi	21,100
at 300 °F	psi	10,400
Flexural Modulus		
at 77 °F	psi	0.56x10 ⁶
at 300 °F	psi	0.32x10 ⁶
Compressive Yield Strength	psi	23,300
Thermal Properties		
Heat Deflection Temperature	°F	345
Weight Loss ²		
30 days at 300 °F	%	0.24
30 days at 400 °F	%	2.90

¹ Cure schedule 2 hours at 300 °F plus 10 hours at 350 °F.

² Weight loss determined on 1/8" x 1/2" x 4" bars aged in a forced draft oven.

Graphite Properties Table 4 / Properties of Graphite Composites¹

<u>Composite Property</u>	<u>Units</u>	<u>Morganite II</u>	<u>Celanese GY-70</u>
Density	g/cm ³	1.57	1.63

Generated: March 28, 2024
Issue Date:
Revision:

© and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Fiber Content, volume percent	Vol. %	69	69
Void Content, volume percent	Vol. %	<2	5
Tensile Strength, psi	psi	152,000	—
Flexure Strength 16:1			
at 77 °F	psi	240,000	101,000
at 180 °F	psi	218,000	—
at 250 °F	psi	132,000	97,000
at 350 °F	psi	82,000	63,000
Interlaminar Shear Strength, Short Beam 5:1			
at 77 °F	psi	11,200	6,300
at 180 °F	psi	10,900	—
at 250 °F	psi	7,400	5,700
at 350 °F	psi	4,700	—
Torsional at 77 °F		12,000	—
Torsional Shear Modulus, psi	psi	0.70 x 10 ⁶	—
Transverse Tensile Strength, psi	psi	5,600	—
Flammability, per ASTM D-635		Self-extinguishing	Self-extinguishing
Burn Time	sec.	27	3

70 tow by pre-pregging and ¹ 15-ply, unidirectional composites were prepared from heat treated Morganite II and Celanese GY-compression molding on a schedule of 2 hours at 275 °F plus 1.5 hours at 350 °F plus 1 hour at 400 °F.

Storage Recommendations regarding storage conditions can be obtained by visiting our web site at www.westlakeepoxy.com

General Information

These are starting formulations and are not proven in the user's particular application but are simply meant to demonstrate the efficacy of the products and to assist in the development of the user's own formulation. It is the user's responsibility to fully-test and qualify the formulation, along with the ingredients, methods, applications or equipment identified herein ("Information"), by the user's knowledgeable formulator or scientist, and to determine the appropriate use conditions and legal restrictions, prior to use of any Information.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Westlake Epoxy products should be directed to your Westlake Epoxy sales representative, or the nearest Westlake Epoxy sales office. Information and MSDSs on non-Westlake Epoxy products should be obtained from the respective manufacturer.

Contact Information

Generated: March 28, 2024
Issue Date:
Revision:

© and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

For product prices, availability, or order placement, please contact customer service:
www.westlakeepoxy.com/Contacts/

For literature and technical assistance, visit our website at www.westlakeepoxy.com

Generated: March 28, 2024
Issue Date:
Revision:

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.