

## Starting Formulation

### SF 1203

Low Temperature Cure, Chemically Resistant Gloss White Enamel  
EPON™ Resin 161 / EPIKURE™ Curing Agent 3292-FX-60

- Features
- Combining ratio of 2:1 by volume
  - Rapid cure for low temperature applications
  - Very good chemical resistance
  - VOC\* level of 2.79 lb/gal (335 g/l)

Formula	<u>Material</u>	<u>Supplier</u>	<u>Pounds</u>	<u>Gallons</u>
Part A				
	EPON Resin 161	Westlake Epoxy	248.5	25.10
	Anti-Terra U Dispersant	BYK-Chemie USA	5.0	0.59
	Beetle® U216-8	Cytec Industries	5.0	0.64
	Thixatrol ST	Elementis Specialties Co.	8.0	1.00
<i>Mix thoroughly, then add</i>				
	R-960 Titanium Dioxide	DuPont Chemical Company	280.0	8.67
	Barytes Barium Sulfate	Harcoros Pigments Inc.	242.0	6.59
	WCD 399 Talc Magnesium Silicate	Whittaker, Clark & Daniels Company	50.0	2.22
<i>High speed disperse to a texture of 7 Hegman. Reduce speed, then add</i>				
	Toluene		23.0	3.19
	Xylene		57.7	8.01
	SilQuest A-1 87	Momentive Performance Materials	5.8	0.65
	Butyl OXITOL® Glycol Ether	Shell Chemical Company	23.0	3.07
	Ektasolve EP 2-Propoxyethanol	Eastman Chemical Company	<u>57.7</u>	<u>6.93</u>
	Total Part A		1005.7	66.66
Part B				
	EPIKURE Curing Agent 3292-FX-60	Westlake Epoxy	<u>283.3</u>	<u>33.34</u>
	Total Part B		283.3	33.34
	Total Part A & B		1289.0	100.00

Generated: March 29, 2024  
Issue Date:  
Revision:

® and ™ Licensed trademarks of Westlake Inc.

#### DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

## Mixing Instructions

	<u>Pounds</u>	<u>Gallons</u>
Part A	1005.7	66.66
Part B	<u>283.3</u>	<u>33.34</u>
Part A + B	1289.0	100.00

## Typical Formulation Table 1 / Formulation Properties Properties

	<u>Units</u>	<u>Value</u>
Mix ratio Part A : Part B	By volume	2 : 1
	By weight	3.54 : 1
Total weight solids	%	78.3
Total volume solids	%	63.7
Volatile Organic Compound (VOC)	lb/gal	2.79
	g/L	335
Induction Time	min.	30
Viscosity @ 25°C		
Part A + Part B	KU	88

Storage Recommendations regarding storage conditions can be obtained by visiting our web site at [www.westlakeepoxy.com](http://www.westlakeepoxy.com)

## General Information

These are starting formulations and are not proven in the user's particular application but are simply meant to demonstrate the efficacy of the products and to assist in the development of the user's own formulation. It is the user's responsibility to fully-test and qualify the formulation, along with the ingredients, methods, applications or equipment identified herein ("Information"), by the user's knowledgeable formulator or scientist, and to determine the appropriate use conditions and legal restrictions, prior to use of any Information.

## Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Westlake Epoxy products should be directed to your Westlake Epoxy sales representative, or the nearest Westlake Epoxy sales office. Information and MSDSs on non-Westlake Epoxy products should be obtained from the respective manufacturer.

## Contact Information

For product prices, availability, or order placement, please contact customer service:

[www.westlakeepoxy.com/Contacts/](http://www.westlakeepoxy.com/Contacts/)

For literature and technical assistance, visit our website at [www.westlakeepoxy.com](http://www.westlakeepoxy.com)

Generated: March 29, 2024  
Issue Date:  
Revision:

© and ™ Licensed trademarks of Westlake Inc.

## DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.