

Starting Formulation

SF 1047

High Solids Red Iron Oxide Epoxy Primer

EPON™ Resin 874-CX-90 / EPIKURE™ Curing Agent 3140

Formula	<u>Material</u>	<u>Supplier</u>	<u>Pounds</u>	<u>Gallons</u>
Part A				
	EPON Resin 874-CX-90	Westlake Epoxy	263.0	28.85
	Beetle U216-8	Cytec Industries.	12.0	1.41
	Xylene	Shell Chemical Company	75.5	10.49
	MIBK	Shell Chemical Company	60.4	9.10
	PGME Acetate		15.1	1.86
	Zinc Phosphate J-0852	Davis Colors	176.5	6.74
	10 ES WOLLASTOCOAT	NYCO Minerals, Inc.	176.5	7.29
	Sparmite	Harcros Pigments Inc.	233.5	6.35
	MicroMica C-3000	KMG Minerals, Inc.	38.8	1.36
	Copperas R-5098	Harcros Pigments Inc.	38.7	0.90
<i>High Speed Disperse to a Texture of 5-6 N. S.</i>				
	Bentone SD-2	Elementis Specialties	<u>9.3</u>	<u>0.65</u>
	Total Part A		1099.3	75.00
Part B				
	EPIKURE Curing Agent 3140	Westlake Epoxy	132.0	16.32
	Xylene	Shell Chemical Company	42.9	5.95
	n-Butanol	Shell Chemical Company	<u>18.4</u>	<u>2.73</u>
	Total Part B		193.3	25.00
	Total Part A & B		1292.6	100.0

Mixing Instructions

	<u>Pounds</u>	<u>Gallons</u>
Part A	1099.3	75.00
Part B	<u>193.3</u>	<u>25.00</u>

Generated: March 28, 2024
Issue Date:
Revision:

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Part A + B	1292.6	100.0
------------	--------	-------

Typical Formulation Table 1 / Formulation Properties
Properties

	<u>Units</u>	<u>Value</u>
Mix ratio Part A : Part B	By volume	3 : 1
	By weight	5.69 : 1.0
Total weight solids	%	81.2
Total volume solids	%	65.4
Pigment volume concentration (PVC)	%	35.0
Volatile Organic Compound (VOC)	lb/gal	2.43
	g/L	292
Induction Time	min.	30
Viscosity @ 25°C		
Part A + Part B	KU	85

Typical Film Table 2 / Film Properties
Properties

Drawdown on CRS. Cured for 7 days at 77 °F and 55% relative humidity.

	<u>Units</u>	<u>Value</u>
Pigment:binder ratio	%	1.72
Curing agent, based on solids	phr	56
Pot life from 85-130 KU	hrs	6
Pounds/gallon	lbs/gal	12.92
Dry film thickness	mils	1.5
Set-to-touch	hrs	1.0
Cotton free	hrs	7.5
Thru-dry	hrs	18.0
Pencil hardness		H
Impact resistance, direct/reverse		52/4
Flexibility		Pass 1/4
Salt spray testing (500 hrs)		2F-2M
Water resistance (500 hrs at 160 °F)		4M
Adhesion		5A

Storage Recommendations regarding storage conditions can be obtained by visiting our web site
at www.westlakeepoxy.com

General Information

Generated: March 28, 2024
Issue Date:
Revision:

© and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

These are starting formulations and are not proven in the user's particular application but are simply meant to demonstrate the efficacy of the products and to assist in the development of the user's own formulation. It is the user's responsibility to fully-test and qualify the formulation, along with the ingredients, methods, applications or equipment identified herein ("Information"), by the user's knowledgeable formulator or scientist, and to determine the appropriate use conditions and legal restrictions, prior to use of any Information.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Westlake Epoxy products should be directed to your Westlake Epoxy sales representative, or the nearest Westlake Epoxy sales office. Information and MSDSs on non-Westlake Epoxy products should be obtained from the respective manufacturer.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.westlakeepoxy.com/Contacts/

For literature and technical assistance, visit our website at www.westlakeepoxy.com

Generated: March 28, 2024
Issue Date:
Revision:

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.