

Starting Formulation

SF 1009

Gloss White Enamel

EPON™ Resin 828 / EPIKURE™ Curing Agent 3175

Formula	Material	Supplier	Pounds	Gallons
Part A				
	EPON Resin 828	Westlake Epoxy	291.1	30.17
	TI-PURE® R960 HG	Du Pont Company	508.4	15.74
	BENTONE® SD-2 Thixotrope	Elementis Specialties Inc.	7.0	0.52
	BUSPERSE® 47, Dispersant/Viscosity Depressant	Buckman Laboratories	2.3	0.31
	EASTMAN® EP, 2-Propoxyethanol	Eastman Chemical Products, Inc.	4.5	0.59
<i>High Speed Disperse to GrindHegman 7-8</i>				
	EASTMAN EP, 2-Propoxyethanol	Eastman Chemical Products, Inc.	123.9	16.34
	BUSPERSE 47, Dispersant/Viscosity Depressant	Buckman Laboratories	2.3	0.31
	Methyl propyl ketone		<u>74.1</u>	<u>11.02</u>
	Total Part A		1,013.6	75.00
Part B				
	EPIKURE Curing Agent 3175	Westlake Epoxy	158.3	19.69
	EASTMAN EP, 2-Propoxyethanol		<u>40.0</u>	<u>5.31</u>
	Total Part B		198.5	25.00
	Total Part A & B		1,212.1	100.00

Mixing Instructions

	Pounds	Gallons
Part A	1,013.6	75.00
Part B	<u>198.5</u>	<u>25.00</u>
Part A + B	1,212.1	100.00

Disperse the pigments in a suitable portion of the vehicle using high speed dispersing equipment. Let down the pigment dispersion with the remaining vehicle. Charge the two ingredients of the curing agent component to a separate suitable container and mix thoroughly. Package the base component and the curing agent component separately to be

Generated: March 28, 2024
Issue Date:
Revision:

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

thoroughly. Package the base component and the curing agent component separately to be combined just prior to use.

Typical Formulation Table 1 / Formulation Properties
Properties

	<u>Units</u>	<u>Value</u>
Mix ratio Part A : Part B	By volume	3 : 1
	By weight	5.11:1.0
Total weight solids	%	80.0
Total volume solids	%	66.7
Pigment volume concentration (PVC)	%	24.4
Volatile Organic Compound (VOC)	lb/gal	2.43
	g/L	292
Induction Time	minutes	30
Potlife	hrs	6
Viscosity @ 25°C		
Part A	KU	64
Part B	KU	61
Part A & B	KU	64

Storage Recommendations regarding storage conditions can be obtained by visiting our web site at www.westlakeepoxy.com

General Information

These are starting formulations and are not proven in the user's particular application but are simply meant to demonstrate the efficacy of the products and to assist in the development of the user's own formulation. It is the user's responsibility to fully-test and qualify the formulation, along with the ingredients, methods, applications or equipment identified herein ("Information"), by the user's knowledgeable formulator or scientist, and to determine the appropriate use conditions and legal restrictions, prior to use of any Information.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Westlake Epoxy, Inc. ("Westlake Epoxy") products should be directed to your Westlake Epoxy sales representative, or the nearest Westlake Epoxy sales office. Information and MSDSs on non-Westlake Epoxy products should be obtained from the respective manufacturer.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.westlakeepoxy.com/Contacts/

For literature and technical assistance, visit our website at www.westlakeepoxy.com

Generated: March 28, 2024
Issue Date:
Revision:

© and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.

® and ™ Licensed trademarks of Westlake Inc.

DISCLAIMER

The information provided herein was believed by Westlake. ("Westlake") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Westlake are subject to Westlake's terms and conditions of sale. WESTLAKE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY WESTLAKE, except that the product shall conform to Westlake's specifications. Nothing contained herein constitutes an offer for the sale of any product.